

DECORATIVE FINISHING PAINT



DESCRIPTION

EFFECT FINISH is a semi-matte decorative finishing paint consisting of a mixture of special acrylic resins and applied on the MIRZASTO, creating a metallic and reflective appearance.

APPLICATION AREA

It is applied as a finishing material on decorative products applied after floor preparation on walls, plasters, gross concretes and wooden surfaces.

SURFACE PREPARATION

After all kinds of dirt, oil, bloated paints and dust are cleaned from the surfaces it will be applied on, surface defects should be smoothened with SAN DECO ACRYLIC PUTTY INTERIOR and primed with SAN DECO DECOPRIMER.

The Product

Composition	Acrylic Based
Density	1.02 g/cm ³
	8,51 lbs./gallon
Storage Temperature	5 °C ÷ 35 °C 41 °F ÷ 95 °F
Emission Limits of Volatile Organic Compounds (VOC) According to Directive 2004/42/CE	Subcategory: L VOC: 40 g/l (max); Limit Phase : 200 g/l
Theoretical Coverage (Single Coat)	651 – 814 sq. Ft/gallon
	16 – 20 m ² /L
Weight Per Gallon	8,51 lbs.
Packaging	1 Quart

FEATURES

- It brings a metallic and shiny appearance into the product to which it is applied.
- It is applied very easily and does not change the texture and pattern of MIRZASTO.
- It can be wiped off with water.
- Due to the strong water vapor permeability, it allows vapor to be released outside and the surface to breathe.
- It is water-based, not harm human health and environment.
- It causes environments of application to smell nice due to its perfume characteristic.

The Application

Dilution	Ready To Use
Surface Preparation	San Deco Acrylic Putty Interior
Primer	San Deco Decoprimer
Application Tools	Trowel
Touch Dry Time	2-3 Hours
Complete Dry Time	24 Hours
Dry Time Temperature	23 °C/73.4°F (relative humidity at 50%)
Application Temperature (24 hours during and after the application)	5 °C ÷ 35 °C 41 °F ÷ 95 °F

APPLICATION INSTRUCTION

- EFFECT FINISH is a product applied on MIRZASTO. EFFECT FINISH starts to be applied 4-5 hours after MIRZASTO is applied in accordance with the instructions.
- After drying is ensured, EFFECT FINISH is applied with a steel trowel or plastic trowel without being diluted at all. It is required to wait at least 2 hours between layers.
- In the EFFECT FINISH application; the excess of the product should thoroughly be removed while the finishing material is applied to extract the patterns and textures on MIRZASTO.
- It should be paid attention that the ambient temperature should be minimum +5°C/41 °F, and maximum +35°C/95 °F within 24 hours during and after the application.

DRYING TIME

At 23°C/73.4°F, the touching time is 2-3 hours and the complete drying time is 24 hours.

THEORETICAL CONSUMPTION

For one-layer application, depending on the surface smoothness, absorbency and application techniques;
-16 – 20 m² with 1 lt.

-15,7 – 19,7 m² area is painted with 1 kg.

- Paint consumption for an area of 1 m² is 50 – 62,5 ml. and 50 – 65 gr.

STORAGE

It can be stored in its unopened package, cool and dry environments, protected from direct sunlight at between +5°C/41 °F and +35°C/95 °F.



HAZARD STATEMENTS

- H317 May cause an allergic skin reaction

PRECAUTIONARY STATEMENTS

- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P272 Contaminated work clothing should not be allowed out of the workplace.
- P280 Wear protective gloves/protective clothing/eye protection/face protection.
- P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
- P333 + P313 If skin irritation or rash occurs: Get medical advice/attention.
- P363 Wash contaminated clothing before reuse.
- EUH208 Contains chloromethylisothiazolinone and methylisothiazolinone (3:1) May produce an allergic reaction.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

Product Technical Data Sheet No. DP. 023.US - Rev01 January 2022

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standards of ISO 9001, ISO 14001, ISO 27001, ISO 45001.